

www.totalfacadesolutions.com



The Elegance of Stainless Steel in Composite Fanel Perfection!



Alubond u.s.a introduces the new technology composite panels in genuine Stainles Steel finishes of brushed (Butler) and high mirror finishes. The natural beauty, flatness and rigidity of stainless steel is now combined with the lightweight, flexible and ease of fabrication of composites making Alubond's Stainless Steel Composites an architects' dream.

#### **Material Composition**

Stainless steel Composite Panel (SCP) is composed of non-combustible mineral filled core and sandwiched between 0.3 mm thick Stainless Steel Sheets grade 304 or 316 of SCP-EX exterior grade stainless steel skin for exterior skin and 0.3 aluminum for back surface. SCP-INT is the interior grade economical version using 0.3 mm. The composite core for this grade is LDPE.

### **Specifications**

Panel thickness	3mm, 4 mm
Core	PE or FR core
Skin thickness	0.3 mm for High Mirror,
	0.4mm for Brushed Hairline
Skin Finishes	High Mirror, Brushed Hairline
Alloy	304, Optional 316
Standard panel size	1220 mm x 2440 mm
Optional Size	
Brushed Hairline	1220 mm x length upto 6000 mm
High Mirror	1220 mm x length upto 6000 mm

#### Typical 4 mm SCP-EX Panel



Non Combustible mineral fi led core 3.4 mm

0.3 mm/0.4mm Stainless Steel

#### Typical 4 mm SCP-INT Panel



#### **Physical Data**

Panel weight SCP-EX Thermal expansion 10.25 kg /m2 for 4mm panel 0.52 mm / m 500C Mechanical properties of SCP

#### **Product Tolerence**

Width	+	2.00 mm
Length	+	4.00 mm
Thickness	+	2.00 mm
Diagnol	+	5.00 mm
Bow	0.5	% of the length or width

**Galvanic corrosion threat:-** Neoprene pads are recommended at the contact point of other metals to stainless steel panels to prevent corrosion.

**Color differences:-** It is recommended that panels should be produced and installed as per one full production lot and in one direction according to the panel's marking to avoid posible color difference from different production lots.







### **Characteristics**

#### **Physical Properties**

Description	ASTM	UNIT	SCM (4mm²)
Specific Gravity			2.50
Weight		Kg/m2	10.20
Thermal expansion	D696	X10°∕°C	10.40
Thermal Conductivity	D976	kcal/m.h.⁰C	0.34
Thermal resistance	D976	m².hr.ºC/kcal	0.19
Deflection Temperature	D648	°C	117.00

#### **Mechanical Properties**

Description	ASTM	UNIT	SCM (4mm²)
Tensile Strength	E8	kg/mm²	8.6
Yield Strength	E8	kg/mm²	7.0
Elongation	E8	%	12.6
Flexural Elasticity	C393	kg/mm²	7200
Flexural Regidity	C393	x10³kg .mm² / mm	38
Punching Shear Resistance Maximum Load (50 mmf) Shear Resistance	D732 D732	kg Kg/mm²	3517 5.6

#### Dent (Impact) test by Du-pointr Method

Steel ball weight	Height	Dent Depth
(Kg)	(mm)	(mm)
0.3	300	0.5
0.5	500	1.1
1.0	300	1.3
1.0	500	1.6

## Mechanical Propetries of Stainless Steel

	ASTM	UNIT	SCM (4mm²)
Surface : YUS220M			
Yield Strength	E8	kg/mm²	30.1
Flexural Elasticity	C393	kg/mm²	20500
Back : SUS430			
Yield Strength	E8	kg/mm²	20.9
Flexural Elasticity	C393	kg/mm²	20400







# **Processing Method**

Alubond u.s.a Stainless Steel processing methods are as follows:

# Cutting

Square shear is suitable for straight cutting and 0.04 mm clearance and 1 30' rake angle. Some of shear droop may occur at the cut edge.

## Grooving

Planer for stainless steel fabrication is required. (Note: Don't use ordinary router or grooving cutter)

# Folding

V -Grooved panels can be folded with folding jig. To ensure a straight line of folded corner, fold the grooved panel on a flat table.

### **Route-in Return System**

Normally, 25 mm from edge is grooved and folded. After assembling, the corner is sealed with the sealant to prevent the corner from water leakage.

# Bending with press brake

When bending Stainless steel Composite Panel with press brake use a top die having the desired radius.

### **Bending with Three Roll Bender**

Three-roll bender enables a larger bending radius than press-brake bending.

### **Reveting & Bolting**

Use stainless steel blind rivet for junction. Fixing work can be done from one direction. Use stainless steel bolt / nut.















For more detailed information and supply of processing tools Alubondu.s.a Engineering can be contacted on techsupport@alubond.com



# Alubond u.s.a Stainless Steel Applications



Entrance Features



Escalator Covers



Column and Signages



Cannopies



Soffit Ceiling



Door Frames and Lift Covers